## **CONCRETO** PRODUCT DATA SHEET



		Concreto	
	Category	Concrete, Floor Tiles, PTV	
		36+ Tiles	$\stackrel{\checkmark}{\frown}$
	Collection	Absolute Collection	- []+
	Short Code	CCR03N	
	Colour	Grey	
	Finish	Natural	$\stackrel{\checkmark}{\frown \uparrow \uparrow}$
Available Sizes	Wall Suitability	Internal & External	
	Floor Suitability	Internal Only	
	Wet Barefoot	-	
608x608x9.5mm 900x450x10mm	Material	Glazed Porcelain	TWK
605x305x7.8mm 330x330x7.2mm	Classificiation	Bla	
55x455x8mm	Light Reflectance Value	38.00	*
	CSV	V4	Æ
	PTV (4S)	Wet 36+ Dry 36+	
Samples Service	PTV (TRL)	-	
Tel: +44 (0)   782 524 043 Fax: +44 (0)   782 577 379	R Value	10	
Email: samples@johnson-tiles.com	Wet Ramp	A	
<b>Technical Helpline</b> Tel: +44 (0)1782 524 111	PEI	IV	kg
Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial	
www.johnson-tiles.com			

 $\mathcal{O}$  Recycled Content

Range

Up to 10%

Concreto

Physio Fest /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
↓ ↑	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\downarrow \\ \uparrow \uparrow$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	Pass
<u> </u>	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
	Thermal Shock EN ISO 10545-9	Pass	Pass
₩	Frost Resistance EN ISO 10545-12	Resistant	Resistant
5	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
کر کی ا	UV Colour Resistance		Unaffected by light
	<b>Fire Rating</b> Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m <sup>2</sup> Thickness: 7.2mm Thickness: 7.8mm Thickness: 8mm		5.78kg   6.9kg   8.39kg
	Thickness: 9.5mm Thickness: 10mm		21.03kg 22.24kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (18/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.

