DANUBE PRODUCT DATA SHEET





Available Sizes 592x592x10.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

	Up to 10%
Range	Danube
Category	Stone, Speckle, Floor Tiles
Collection	Absolute Collection
Short Code	DAN03L
Colour	Grey
Finish	Lapato
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classificiation	Bla
Light Reflectance Value	39.00
CSV	V2
PTV (4S)	Wet 0-24 Dry 36+
PTV (TRL)	-
R Value	-
Wet Ramp	-
PEI	IV
Traffic	Commercial

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%	
Straightness of Si EN ISO 10545-2	des ±0.5% ≤ ± 1.5mm	±0.3%	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
Water Absorption EN ISO I 0545-3	1 ≤0.5%	≤0.1%	
Modulus of Ruptu EN ISO 10545-4	ire ≥35N/mm²	≥35N/mm²	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistar EN ISO 10545-13	nce Min Class B	Class A	
Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
UV Colour Resista	ance	Unaffected by light	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
Weight/m² Thickness:9mm Thickness:10.5mm	1	21.78kg 27.32kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a lay slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (18/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in Englance. No. 15600437. © 2024 Johnson Tiles All rights reserved.

