CANVAS PRODUCT DATA SHEET



arnothing Recycled Content	Up to 40%	
Range	Canvas	
Category	Stone, Marble, Structure	
Collection	Select Collection	
Short Code	CAV05D	
Colour	Grey	
Finish	Matt - Chevron Structure	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
Light Reflectance Value	55.00	
CSV	V3	

Physical Properties			
Test / S	tandard	Requirement	Test Result
	L ength/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass
	Thickness EN ISO 10545-2	±10%≤±0.5mm	Pass
- +	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
(Water Absorption EN ISO 10545-3	10% to 20%	> 10%
	Modulus of Rupture EN ISO 10545-4	Ave I5N/mm ²	Pass
7 3	Thermal Shock EN ISO 10545-9	Pass	Pass
75	F rost Resistance Not Applicable	N/A	Not suitable
(A)	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass
22 20 20 20 20 20 20 20 20 20 20 20 20 2	UV Colour Resistance		Unaffected by light
	Fire Rating		Class A1 Non Combustible
NS I	Weight/m² Thickness 8.5mm		14.6kg

Available Sizes 600x300x8.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (15/03/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent, ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

JOHNSON TILES

epd