


SLOAN PRODUCT DATA SHEET



Available Sizes

600x600x10.5mm
600x300x10.5mm
1200x600x10.5mm
1200x1200x10.5mm

Samples Service














Tel: +44 (0)1782 524 043
Fax: +44 (0)1782 577 379
Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111
Fax: +44 (0)1782 577 379
Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Range	Sloan
Category	Stone, Floor Tiles
Collection	Absolute Collection
Short Code	SLN05N
Colour	Cloud
Finish	Natural
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Un-glazed Porcelain
Classification	Bla
Light Reflectance Value	45.00
CSV	V2
PTV (96)	Wet 0-24 Dry 36+
PTV (55)	-
R Value	10
Wet Ramp	A
PEI	-
Traffic	Commercial

Physical Properties			
Test / Standard		Requirement	Test Result
	Length/Width EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
	Thickness EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
	Straightness of Sides EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
	Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
	Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
	Water Absorption EN ISO 10545-3	$\leq 0.5\%$	$\leq 0.1\%$
	Modulus of Rupture EN ISO 10545-4	$\geq 35\text{N/mm}^2$	$\geq 45\text{N/mm}^2$
	Thermal Shock EN ISO 10545-9	Pass	Pass
	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
	Weight/m² Thickness: 10.5mm		25.25kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (13/03/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

Est. 1901
**JOHNSON
TILES**