

DAKOTA

GLAZED CERAMIC AND PORCELAIN | WALL AND FLOOR TILES

STONE SELECT



www.johnson-tiles.com

© 2024 Johnson Tiles Limited

Est. 1901
**JOHNSON
TILES**


DAKOTA

 **THREE COLOURS**

 **TWO SIZES**

 **TWO FINISHES**

Introducing Dakota, our new stone-effect glazed ceramic wall tile range, offering a stunning and realistic alternative to natural stone. The two large-format sizes of 600x300mm and 600x600mm makes them perfect for any residential or commercial application, creating a visually striking impact on any wall or floor. The mineral vein detailing alongside glossy inkjet prints provides a delicate shimmer with a matt finish, creating a naturalistic look that is reminiscent of real stone, adding depth and character to any space and creating a harmonious blend of nature and modernity. The low maintenance requirements and timeless, classic colour palette of Sand, Pebble and Basalt, ensure they will continue to look stunning for years to come. As a versatile and stylish option, Dakota is sure to enhance any interior design scheme.





Wall: Sand Matt 600x300x8mm - DAK01A
Floor: Sand Matt 600x600x9mm - DAK01F



Pebble Matt 600x300x8mm - DAK02A



Pebble Matt 600x300x8mm - DAK03A



Wall: Pebble Matt 600x300x8mm - DAK02A
Floor: Basalt Matt 600x600x9mm - DAK03F

COLOURS AND PRODUCT CODES

V2: Low to Moderate Shade Variation




SAND PEI: IV LRV: 62

Product Code (BIII): M DAK01A | Product Code (BIa): M DAL01F



PEBBLE PEI: III LRV: 54

Product Code (BIII): M DAK02A | Product Code (BIa): M DAL02F



BASALT PEI: III LRV: 18

Product Code (BIII): M DAK03A | Product Code (BIa): M DAL03F

SIZE FORMATS AND AVAILABILITY

Size Options and Packing Information



#	Size Format	Thickness	Finish	Structure	Availability	Class	Pcs / Box	M ² / Box	Kg / Box
01	600x300mm	8mm	M Matt	-	All Colours Shown	BIII	6 Tiles	1.08 m ²	16.00 kg
02	600x600mm	9mm	M Matt	-	All Colours Shown	Bla	4 Tiles	1.44 m ²	29.00 kg

Note: Glazed Ceramic / BIII and Glazed Porcelain / Bla tiles. For more information please see the suitability advice given in the technical section. All sizes indicated are metric modular. All sizes shown are nominal. For the most up-to-date size, colour and finish availability, please visit our website - www.johnson-tiles.com. (R) Rectified Edge.





Wall: Pebble Matt 600x300x8mm - DAK02A
 Floor: Basalt Matt 600x600x9mm - DAK03F


TECHNICAL SUPPORT

Specification, Sustainability and Important Information














Product Specification

Range Name	Finish	Structure	Wall Suitability	Floor Suitability	Wet Barefoot	Material / Class
Dakota	 Matt	-	Internal Only	-	-	Glazed Ceramic / BIII
	 Matt	-	Internal and External	Internal Only	-	Glazed Porcelain / BIIa














Floor Values

Finish	Structure	Colour	PTV (96)	PTV (55)	R Value	Wet Ramp	PEI	Traffic
 Matt	-	Sand	Wet 25 - 35	-	-	-	IV	Commercial
		Pebble and Basalt	Wet 25 - 35	-	-	-	III	Light Commercial

Physical Properties - Glazed Ceramic / BIII

Test and Standard	Requirement	Result	Test and Standard	Requirement	Result
 Length / Width EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Modulus of Rupture EN ISO 10545-4	Min. 15N / mm ²	Pass
 Thickness EN ISO 10545-2	$\pm 10\% \leq \pm 0.5\text{mm}$	Pass	 Thermal Shock EN ISO 10545-9	Pass	Pass
 Straightness of Side EN ISO 10545-2	$\pm 0.3\% \leq \pm 1.5\text{mm}$	Pass	 Frost Resistance EN ISO 10545-12	-	Not Suitable
 Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Chemical Resistance EN ISO 10545-13	Min. Class B	Pass
 Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Stain Resistance EN ISO 10545-14	Min. Class 3	Pass
 Water Absorption EN ISO 10545-3	10% to 20%	Pass	 Fire Rating		Class A I Non Combustible
 Weight / M ²	14.82 kg 8mm Thick				

Physical Properties - Glazed Porcelain / BIIa

Test and Standard	Requirement	Result	Test and Standard	Requirement	Result
 Length / Width EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass	 Modulus of Rupture EN ISO 10545-4	Min. 35N / mm ²	Pass
 Thickness EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass	 Thermal Shock EN ISO 10545-9	Pass	Pass
 Straightness of Side EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass	 Frost Resistance EN ISO 10545-12	Resistant	Resistant
 Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Chemical Resistance EN ISO 10545-13	Min. Class B	Pass
 Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Stain Resistance EN ISO 10545-14	Min. Class 3	Pass
 Water Absorption EN ISO 10545-3	$\leq 0.5\%$	Pass	 Fire Rating		Class A I FL Non Combustible
 Weight / M ²	20.14 kg 9mm Thick				

Sustainability Credentials

Range Name	Material / Class	EPD	Recycled Content - Tiles	Recycled Content - Packaging
Dakota	Glazed Ceramic / BIII	Yes	Up to 20%	Up to 100% (Boxes Only)
	Glazed Porcelain / BIIa	Yes	Up to 40%	Up to 100% (Boxes Only)

Note: Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. Given this, please refer to our website for the most up-to-date information. The slip resistance properties of a surface can only be maintained with the implementation of an effective regular cleaning and maintenance regime. The frequency of cleaning should be determined by the property manager based on the potential level of surface contaminants. The need for an additional regular cleaning and maintenance regime is further heightened when tiles are used for external floor and wet barefoot applications. Please contact our technical helpline, or visit our website for specification and installation advice. All floor tiles shown in this literature achieve a PTV (96) Dry 36+ test result. PTV (96): Pendulum Test Value - 4S. PTV (55): Pendulum Test Value - TRL. R Value (DIN 51130). Wet Ramp (DIN 51097). PEI: Porcelain Enamel Institute. EPD: Environmental Product Declaration. CSV: Colour Shade Variation.

TECHNICAL SUPPORT

Specification, Sustainability and Important Information

Important Information

During the manufacturing process of ceramic and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour and patterning are acceptable.

The tiles shown in this literature are quality products and conform to BS EN 14411 as shown in the physical properties listed above.

For a comprehensive colour, size, finish and availability overview along with full technical and sustainability information for all products shown, please visit our website - www.johnson-tiles.com

- All sizes listed are metric modular.
- For specific suitability details, please contact our technical advice helpline or use the email address provided.
- Johnson Tiles Limited cannot accept responsibility for any tiles that have already been fixed.
- Johnson Tiles Limited reserves the right to change specification and availability information without prior notice.
- Nothing in these statements does or will affect the statutory rights of the consumer.

All product technical values quoted in this literature are supported by laboratory testing from our own and independent ceramic test houses. Johnson Tiles Limited are British Standard registered. To find out more, please contact our technical advice helpline on +44 (0)1782 524 111 or email: ddunlop@johnson-tiles.com.



Wall: Sand Matt 600x300x8mm - DAK01A
Floor: Sand Matt 600x600x9mm - DAK01F

WHERE TO FIND US

Head Office

Harewood Street, Tunstall,
Stoke on Trent, Staffordshire,
ST6 5JZ, United Kingdom

Tel: +44 (0)1782 575 575
Email: info@johnson-tiles.com
www.johnson-tiles.com

Material Lab Studio

10 Great Titchfield Street,
London, W1W 8BB,
United Kingdom

Tel: +44 (0)20 7436 8629
Email: info@material-lab.co.uk
www.material-lab.co.uk

Factory Outlet

Tel: +44 (0)1782 524 040
Email: foutlet@johnson-tiles.com
www.outlet.johnson-tiles.com

Customer Services

Tel: +44 (0)1782 524 000
Email: sales@johnson-tiles.com
8:30am - 5:00pm (Monday - Friday)

Order A Sample

Tel: +44 (0)1782 524 043
Email: samples@johnson-tiles.com

Technical Advice Helpline

Tel: +44 (0)1782 524 111
Email: ddunlop@johnson-tiles.com

Updated: September 2024



www.johnson-tiles.com | [f](#) [X](#) [G](#) [d](#) [P](#) [in](#) [v](#)

© 2024 Johnson Tiles Limited