

ZIBBO

GLAZED PORCELAIN | FLOOR AND WALL TILES

WOOD ABSOLUTE



www.johnson-tiles.com

© 2024-25 Johnson Tiles Limited

Est. 1901
**JOHNSON
TILES**

ZIBBO



SEVEN COLOURS



THREE SIZES



ONE FINISH

Offering a stunningly realistic woodgrain surface effect and taking inspiration from the natural world, Zibbo perfectly replicates the beauty of the forest. Featuring three large-format sizes – including traditional 1500x250mm and 1200x200mm planks, along with a unique 1200x600mm option, all available in a single hard-wearing Grip finish. With a wide selection of colours available, from the muted tones of White, Bone and Silver to the deeper, richer shades of Mid Oak and Dark Oak, and a PTV 36+ slip resistance rating for both internal and external use you can be assured that Zibbo has you covered for all application types.





Dark Grey Grip 1200x200x9mm - ZBB07G




Light Oak Grip 1500x250x9mm - ZBB04G

COLOURS AND PRODUCT CODES

V2: Low to Moderate Shade Variation




WHITE PEI: IV LRV: 53

Product Code:  ZBB01G




BONE PEI: IV LRV: 52

Product Code:  ZBB02G



SILVER PEI: IV LRV: 38

Product Code:  ZBB03G



LIGHT OAK PEI: IV LRV: 39

Product Code:  ZBB04G


COLOURS AND PRODUCT CODES

V2: Low to Moderate Shade Variation



MID OAK PEI: III LRV: 23

Product Code:  ZBB05G



DARK OAK PEI: III LRV: 22

Product Code:  ZBB06G



DARK GREY PEI: IV LRV: 29

Product Code:  ZBB07G



Bone Grip 1500x250x9mm - ZBB02G

SIZE FORMATS AND AVAILABILITY

Size Options and Packing Information

01






02



03



#	Size Format	Thickness	Finish	Availability	Class	Pcs / Box	M ² / Box	Kg / Box
01	1500x250mm	9mm	 Grip	All Colours Shown	Bla	4 Tiles	1.50 m ²	35.00 kg
02	1200x600mm	10.5mm	 Grip	All Colours Shown	Bla	2 Tiles	1.44 m ²	29.50 kg
03	1200x200mm	9mm	 Grip	All Colours Shown	Bla	7 Tiles	1.68 m ²	32.00 kg

Note: Glazed Porcelain / Bla tiles. For more information please see the suitability advice given in the technical section. All sizes indicated are metric modular. All sizes shown are nominal. For the most up-to-date size, colour and finish availability, please visit our website - www.johnson-tiles.com. (R) Rectified.




Mid Oak Grip 1500x250x9mm - ZBB05G


TECHNICAL SUPPORT

Specification, Sustainability and Important Information













Product Specification

Range Name	Finish	Wall Suitability	Floor Suitability	Wet Barefoot	Material / Class
Zibbo	 Grip	Internal and External	Internal and External	Yes	Glazed Porcelain / Bla

Floor Values

Finish	Colour	PTV (96)	PTV (55)	R Value	Wet Ramp	PEI	Traffic
 Grip	Mid Oak and Dark Oak Only	Wet 36+	Wet 36+	R 11	-	III	Light Commercial
	All Other Colours	Wet 36+	Wet 36+	R 11	-	IV	Commercial

Physical Properties - Glazed Porcelain / Bla

Test and Standard	Requirement	Result	Test and Standard	Requirement	Result
 Length / Width EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass	 Modulus of Rupture EN ISO 10545-4	Min. 35N / mm ²	Pass
 Thickness EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass	 Thermal Shock EN ISO 10545-9	Pass	Pass
 Straightness of Side EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass	 Frost Resistance EN ISO 10545-12	Resistant	Resistant
 Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Chemical Resistance EN ISO 10545-13	Min. Class B	Pass
 Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass	 Stain Resistance EN ISO 10545-14	Min. Class 3	Pass
 Water Absorption EN ISO 10545-3	$\leq 0.5\%$	Pass	 Fire Rating		Class A I FL Non Combustible

Sustainability Credentials

Range Name	Material / Class	EPD	Recycled Content - Tiles	Recycled Content - Packaging
Zibbo	Glazed Porcelain / Bla	Yes	Up to 40%	Up to 100% (Boxes Only)

Note: Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. Given this, please refer to our website for the most up-to-date information. The slip resistance properties of a surface can only be maintained with the implementation of an effective regular cleaning and maintenance regime. The frequency of cleaning should be determined by the property manager based on the potential level of surface contaminants. The need for an additional regular cleaning and maintenance regime is further heightened when tiles are used for external floor and wet barefoot applications. Please contact our technical helpline, or visit our website for specification and installation advice. All floor tiles shown in this literature achieve a PTV (96) Dry 36+ test result. PTV (96): Pendulum Test Value - 4S. PTV (55): Pendulum Test Value - TRL. R Value (DIN 51130). Wet Ramp (DIN 51097). PEI: Porcelain Enamel Institute. EPD: Environmental Product Declaration. CSV: Colour Shade Variation.

Important Information

During the manufacturing process of ceramic and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour and patterning are acceptable.

The tiles shown in this literature are quality products and conform to BS EN 14411 as shown in the physical properties listed above.

For a comprehensive colour, size, finish and availability overview along with full technical and sustainability information for all products shown, please visit our website - www.johnson-tiles.com

- All sizes listed are metric modular.
- For specific suitability details, please contact our technical advice helpline or use the email address provided.
- Johnson Tiles Limited cannot accept responsibility for any tiles that have already been fixed.
- Johnson Tiles Limited reserves the right to change specification and availability information without prior notice.
- Nothing in these statements does or will affect the statutory rights of the consumer.

All product technical values quoted in this literature are supported by laboratory testing from our own and independent ceramic test houses. Johnson Tiles Limited are British Standard registered. To find out more, please contact our technical advice helpline on +44 (0)1782 524 111 or email: technical@johnson-tiles.com.

WHERE TO FIND US

Head Office

Harewood Street, Tunstall,
Stoke on Trent, Staffordshire,
ST6 5JZ, United Kingdom

Tel: +44 (0)1782 575 575
Email: info@johnson-tiles.com
www.johnson-tiles.com

Material Lab Studio

10 Great Titchfield Street,
London, W1W 8BB,
United Kingdom

Tel: +44 (0)20 7436 8629
Email: info@material-lab.co.uk
www.material-lab.co.uk

Factory Outlet

Tel: +44 (0)1782 524 040
Email: foutlet@johnson-tiles.com
www.outlet.johnson-tiles.com

Customer Services

Tel: +44 (0)1782 524 000
Email: sales@johnson-tiles.com
8:30am - 4:30pm (Monday - Friday)

Order A Sample

Tel: +44 (0)1782 524 043
Email: samples@johnson-tiles.com

Technical Advice Helpline

Tel: +44 (0)1782 524 111
Email: technical@johnson-tiles.com

Updated: February 2025



www.johnson-tiles.com | [f](#) [X](#) [G](#) [d](#) [P](#) [in](#) [v](#)

© 2024-25 Johnson Tiles Limited