HEX25

GLAZED PORCELAIN | FLOOR AND WALL TILES

























f X ⊙ ♂ P in □ www.johnson-tiles.com © 2024 Johnson Tiles Limited



HEX25








Hex25 offers a contemporary colour palette of muted tones coupled with richer vibrant colours. Thirteen base field colours are available in a small format hexagon to deliver geometric patterning. Four décor options are also featured, allowing creativity and flair to come to the fore with designs such as Trident and Aster.









COLOURS AND PRODUCT CODES

VI: Low Shade Variation




COLOURS AND PRODUCT CODES

VI: Low Shade Variation







ASTER BLANCO PEI: IV Product Code: N HEX16F





TRIDENT BLANCO PELIV

Product Code: N HEX17F



FANTASY MIX PEI: IV

Product Code: N HEX19F



KASBAH MIX PEI: IV


Product Code: N HEX22F

Note: Each box of Kasbah Mix HEX22F contains a random mix of twenty-four colour/design options like the one shown above.



SIZE FORMATS AND AVAILABILITY

Size Options and Packing Information



#	Size Format	Thickness	Finish	Availability	Class	Pcs / Box	M² / Box	Kg / Box
01	250x220mm Hexagon	1.0	N Natural	All Colours Shown	Bla	25 Tiles	1.05 m ²	24.00 kg
01	230x220mm Hexagon	I0mm	G Antislip	White, Silver and BlackOnly	Bla	25 Tiles	1.05 m²	24.00 kg

Note: Glazed Porcelain / Bla tiles. For more information please see the suitability advice given in the technical section. All sizes indicated are metric modular. All sizes shown are nominal. For the most up-to-date size, colour and finish availability, please visit our website - www.johnson-tiles.com.



06 www.johnson-tiles.com

TECHNICAL SUPPORT

Specification, Sustainability and Important Information

Product Specification

Range Name	Finish	Wall Suitability	Floor Suitability	Wet Barefoot	Material / Class
Hex25	N Natural	Internal and External	Internal Only	-	Glazed Porcelain / Bla
пех25	A Antilsip	Internal and External	Internal Only	-	Glazed Porcelain / Bla

Floor Values

Finish	Colour	PTV (96)	PTV (55)	R Value	Wet Ramp	PEI	Traffic
N Natural	Black, Kale, Moss, Mid Blue and Red Only	Wet 0 - 24	-	R9	-	III	Light Commercial
[N] Natural	All Other Colours	Wet 0 - 24	-	R9	-	IV	Commercial
A - +:-l:-	Black, Kale, Moss, Mid Blue and Red Only	Wet 36+	-	RIO	-	III	Light Commercial
A Antislip	All Other Colours	Wet 36+	-	RIO	-	IV	Commercial

Physical Properties - Glazed Porcelain / Bla

Test and Standard	Requirement	Result	Test and Standard Requirement R	esult
Length / Width EN ISO 10545-2	± 0.6% ≤ ± 2mm	Pass	Modulus of Rupture Min. 35N / mm² Pa	ass
Thickness EN ISO 10545-2	± 5% ≤ ± 0.5mm	Pass	Thermal Shock Pass Pa	ass
Straightness of Side EN ISO 10545-2	± 0.5% ≤ ± 1.5mm	Pass	Frost Resistance Resistant Re	esistant
Rectangularity EN ISO 10545-2	± 0.5% ≤ ± 2mm	Pass	Chemical Resistance EN ISO 10545-13 Min. Class B Pa	ass
Surface Flatness EN ISO 10545-2	± 0.5% ≤ ± 2mm	Pass	Stain Resistance Min. Class 3 Pa	ass
Water Absorption EN ISO 10545-3	≤ 0.5%	Pass	M Fire Rating	lass AIFL on Combustible

Sustainability Credentials

Range Name	Material / Class	EPD	Recycled Content - Tiles	Recycled Content - Packaging
Hex25	Glazed Porcelain / Bla	-	Up to 10%	Up to 100% (Boxes Only)

Note: Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. Given this, please refer to our website for the most up-to-date information. The slip resistance properties of a surface can only be maintained with the implementation of an effective regular cleaning and maintenance regime. The frequency of cleaning should be determined by the property manager based on the potential level of surface contaminants. The need for an additional regular cleaning and maintenance regime is further heightened when tiles are used for external floor and wet barefoot applications. Please contact our technical helpline, or visit our website for specification and installation advice. All floor tiles shown in this literature achieve a PTV (96) Dry 36+ test result. PTV (96): Pendulum Test Value - 4S. PTV (55): Pendulum Test Value - 4S. PTV (55): Pendulum Test Value - TRL. R Value (DIN 51130). Wet Ramp (DIN 51097). PEI: Porcelain Enamel Institute. EPD: Environmental Product Declaration. CSV: Colour Shade Variation.

Important Information

During the manufacturing process of ceramic and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour and patterning are acceptable.

The tiles shown in this literature are quality products and conform to BS EN 14411 as shown in the physical properties listed above.

For a comprehensive colour, size, finish and availability overview along with full technical and sustainability information for all products shown, please visit our website - www.johnson-tiles.com

- All sizes listed are metric modular.
- For specific suitability details, please contact our technical advice helpline or use the email address provided.
- Johnson Tiles Limited cannot accept responsibility for any tiles that have already been fixed.
- Johnson Tiles Limited reserves the right to change specification and availability information without prior notice.
- Nothing in these statements does or will affect the statutory rights of the consumer.

All product technical values quoted in this literature are supported by laboratory testing from our own and independent ceramic test houses. Johnson Tiles Limited are British Standard registered. To find out more, please contact our technical advice helpline on +44 (0) 1782 524 111 or email: technical@johnson-tiles.com.

7 www.johnson-tiles.com

WHERE TO FIND US

Head Office

Harewood Street, Tunstall, Stoke on Trent, Staffordshire, ST6 5JZ, United Kingdom

Tel: +44 (0) 1782 575 575 Email: info@johnson-tiles.com www.johnson-tiles.com

Material Lab Studio

10 Great Titchfield Street, London, WIW 8BB, United Kingdom

Tel: +44 (0)20 7436 8629 Email: info@material-lab.co.uk www.material-lab.co.uk

Factory Outlet

Tel: +44 (0) 1782 524 040 Email: foutlet@johnson-tiles.com www.outlet.johnson-tiles.com

Customer Services

Tel: +44 (0) 1782 524 000 Email: sales@johnson-tiles.com 8:30am - 4:30pm (Monday - Friday)

Order A Sample

Tel: +44 (0) 1782 524 043 Email: samples@johnson-tiles.com

Technical Advice Helpline

Tel: +44 (0) 1782 524 111 Email: technical@johnson-tiles.com JOHNSON TILES

www.johnson-tiles.com | f × ② & 9 in □